



Natural Stone Solutions™

"Real Stone for Real Professionals"™

www.nssthinstone.com

Specifications – Rustic Ledgestone

November-09

Amber Wood Rustic Ledgestone™

Geology: Sandstone

Thickness: 0.75"-1.75"

Size Range: 1"-5" heights, 6"-16" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 165.0 lbs./cu. ft.

Blue Ridge Rustic Ledgestone™

Geology: Quartzitic Sandstone

Thickness: 0.75"-1.75"

Size Range: 1"-4" heights, 6"-16" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 162.7 lbs./cu. ft.

Absorption (ASTM C97): 1.08%

Compressive Strength (ASTM C170): Parallel to Rift (dry) 14,482 psi

Compressive Strength (ASTM C170): Perpendicular to Rift (dry) 18,386 psi

Modulus of Rupture (ASTM C99): Perpendicular to Rift (dry) 2,856 psi

Briar Cliff Rustic Ledgestone™

Geology: Quartzitic Sandstone

Thickness: 0.75"-1.75"

Size Range: Approx. 1"-4" heights, 6"-18" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 163.5 lbs./cu. ft.

Chardonnay Rustic Ledgestone™

Geology: Quartzitic Sandstone

Thickness: 0.75"-1.75"

Size Range: 2"-5" heights, 6"-18" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 165.0 lbs./cu. ft.

Absorption (ASTM C97): 0.72%

Compressive Strength (ASTM C170): Parallel to Rift (dry) 16,610 psi

Compressive Strength (ASTM C170): Perpendicular to Rift (dry) 10,770 psi

Modulus of Rupture (ASTM C99): Perpendicular to Rift (dry) 650 psi



Natural Stone Solutions™

"Real Stone for Real Professionals"™

www.nssthinstone.com

Specifications – Rustic Ledgestone

November-09

Golden Porter Rustic Ledgestone™

Geology: Sandstone

Thickness: 0.75"-1.75"

Size Range: 1"-4" heights, 6"-16" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 166.8 lbs./cu. ft.

Absorption (ASTM C97): 0.45%

Compressive Strength (ASTM C170): Parallel to Rift (dry) 16,700 psi

Compressive Strength (ASTM C170): Perpendicular to Rift (dry) 16,230 psi

Modulus of Rupture (ASTM C99): Perpendicular to Rift (dry) 2,590 psi

Grist Mill Rustic Ledgestone™

Geology: Quartzitic Sandstone

Thickness: 0.75"-1.75"

Size Range: 1"-4" heights, 6"-16" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 162.7 lbs./cu. ft.

Absorption (ASTM C97): 1.08%

Compressive Strength (ASTM C170): Parallel to Rift (dry) 14,482 psi

Compressive Strength (ASTM C170): Perpendicular to Rift (dry) 18,386 psi

Modulus of Rupture (ASTM C99): Perpendicular to Rift (dry) 2,856 psi

Lincoln Creek Rustic Ledgestone™

Geology: Quartzitic Sandstone

Thickness: 0.75"-1.75"

Size Range: 3"-6" heights, 6"-18" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 165.0 lbs./cu. ft.

Olcott Rustic Ledgestone™

Geology: Quartzitic Sandstone

Thickness: 0.75"-1.75"

Size Range: Approx. 2"-5" heights, 6"-18" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 163.5 lbs./cu. ft.

Absorption (ASTM C97): 0.28%

Compressive Strength (ASTM C170): Parallel to Rift (dry) 25,850 psi

Compressive Strength (ASTM C170): Perpendicular to Rift (dry) 16,040 psi

Modulus of Rupture (ASTM C99): Perpendicular to Rift (dry) 830 psi



Natural Stone Solutions™

"Real Stone for Real Professionals"™

www.nssthinstone.com

Specifications – Rustic LedgeStone

November-09

Old Barn Rustic LedgeStone™

Geology: Quartzitic Sandstone

Thickness: 0.75"-1.75"

Size Range: Approx. 1"-4" heights, 4"-14" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 163.5 lbs./cu. ft.

Regal Rustic LedgeStone™

Thickness: 0.75"-1.75"

Size Range: 2"-5" heights, 6"-18" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 165.0 lbs./cu. ft.

Shawnee Mountain Rustic LedgeStone™

Geology: Sandstone

Thickness: 0.75"-1.75"

Size Range: 2"-5" heights, 4"-14" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 156 lbs./cu. ft.

Absorption (ASTM C97): 1.9%

Compressive Strength (ASTM C170): 16,550 psi

Flexural Strength (ASTM C880): 1,580 psi

Susquehanna Rustic LedgeStone™

Geology: Quartzitic Sandstone

Thickness: 0.75"-1.75"

Size Range: 2"-5" heights, 4"-14" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 162.7 lbs./cu. ft.

Absorption (ASTM C97): 1.08%

Compressive Strength (ASTM C170): Parallel to Rift (dry) 14,482 psi

Compressive Strength (ASTM C170): Perpendicular to Rift (dry) 18,386 psi

Modulus of Rupture (ASTM C99): Perpendicular to Rift (dry) 2,856 psi

Wheatfield Rustic LedgeStone™

Geology: Quartzitic Sandstone

Thickness: 0.75"-1.75"

Size Range: 3"-6" heights, 6"-18" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 165.0 lbs./cu. ft.



Natural Stone Solutions™

"Real Stone for Real Professionals"™

www.nsthinstone.com

Specifications – Rustic Ledgerstone

November-09

Wheatfield Tumbled Rustic Ledgerstone™

Thickness: 0.75"-1.75"

Size Range: 2"-5" heights, 6"-18" lengths

Weight: Typically 13 lbs./sq. ft.

Density (ASTM C97): 165.0 lbs./cu. ft.